


IRON OXIDE - HEMATITE

Fe₂O₃

CAS N°: 1309-37-1

MAIN CHARACTERISTICS																
Characteristics	Units	Results														
Colour Structure Carr Index (flowability) IC < 15 % : excellent 15 < IC < 25 % : medium IC > 25 % : bad	NA NA %	Red powder Rhomboedral /														
PARTICLE SIZE DISTRIBUTION		CHEMICAL COMPOSITION														
 <p>Volume (%)</p> <p>(µm)</p> <p>d(10) = 0.32 µm d(50) = 0.66 µm d(90) = 1.28 µm</p>		<table> <tr><td>Ca</td><td>< 5ppm</td></tr> <tr><td>K</td><td>< 5ppm</td></tr> <tr><td>Cu</td><td>< 15ppm</td></tr> <tr><td>Mn</td><td>< 50ppm</td></tr> <tr><td>Na</td><td>< 5ppm</td></tr> <tr><td>Pb</td><td>< 10ppm</td></tr> <tr><td>Zn</td><td>< 10ppm</td></tr> </table>	Ca	< 5ppm	K	< 5ppm	Cu	< 15ppm	Mn	< 50ppm	Na	< 5ppm	Pb	< 10ppm	Zn	< 10ppm
Ca	< 5ppm															
K	< 5ppm															
Cu	< 15ppm															
Mn	< 50ppm															
Na	< 5ppm															
Pb	< 10ppm															
Zn	< 10ppm															

Every material proposed by Marion Technologies can be adjusted according to your specifications in order to meet your needs.

If you require any information or quote, please do not hesitate to contact us.

www.mariontechnologies.com